

EPOXY PRIMER

TWO COMPONENT WATER DISPERSIBLE PRIMER



DESCRIPTION

A non-flammable, two component water dispersible epoxy primer containing exact quantities of resin and hardener, ready for mixing together. Curing is by chemical reaction, producing a semi-gloss film finish. The primer is coloured to identify coated areas.

USES

Screedmaster Epoxy Primer can be used as a primer/ bonding agent prior to the application of any of the Screedmaster range of smoothing compounds. It can be used on all smooth and dense surfaces, power floated concrete, ceramic tiles, quarry tiles, terrazzo, rigid metal, asphalt and surface membranes.

Screedmaster Epoxy Primer may be used as a barrier primer on anhydrite (calcium sulphate) screeds prior to application of cementitious materials: please contact Flooring Technical Services.

PREPARATION

Relevant Standards:

All phases of the installation should comply with the latest editions of the following standards:

BS 8102 Code of Practice for protection of buildings against water from the ground.

BS 8203 Code of Practice for installation of resilient floor coverings.

BS 5325 Code of Practice for installation of textile floor coverings.

SUB-FLOOR

The sub-floor should be clean, structurally sound, dry and free from all contaminants, including surface hardeners and additives that may hinder adhesion. It should also have an effective structural damp-proof membrane and be suitably dry. The only British Standard approved test for dryness is by properly calibrated and insulated hygrometer giving a reading less than 75% RH.

Where this has not been achieved the use of a suitable Screedmaster surface membrane will suppress residual moisture in a power floated concrete slab or sand/cement screed provided that a base DPM has been incorporated.

Please refer to the relevant data sheets for full information.

2 PART EPOXY PRIMER

WATER DISPERSIBLE

EXCEPTIONAL ADHESION

SUITABLE FOR ALL SUBFLOOR TYPES

FOR USE AS A BONDING AID

TYPE OF SOLVENT
Part A Solvent free Part B Water based
APPROX. FLASHPOINT
Part A > 150°C Part B Non flammable
APPROX. COVERAGE
50 to 60 m ² (on smooth surfaces)
APPLICATION TEMP. LIMITS
5°C to 40°C
DRYING TIME
overnight (13°C or above)
SIZES AVAILABLE
6kg unit (5kg resin and 1kg hardener)

MIXING

Mix the two components together, adding hardener B to resin A until a completely uniform colour is obtained, using an electric drill and propeller blade. The components should not be mixed together until application is ready to start, and should be applied as soon as mixing has been completed. **ANY UNMIXED MATERIAL WILL NOT HARDEN.**

APPLICATION

The mixed material should be applied by brush or lambswool roller ensuring that the primer is well worked into the surface. As soon as it has become transparent, i.e. when the primer is tacky but not wet, the appropriate Screedmaster Smoothing Compound may be applied. Keep the area dust free until the smoothing compound is applied. For best results leave to dry for 12 hours. If the primed surface is left for longer than 24 hours it may lose its tack and may require a repeat application.

DRYING CONDITIONS

Screedmaster Epoxy Primer will cure between 6 and 24 hours of application depending upon substrate, temperature and ventilation. Under cold conditions the curing rate will be considerably slower. The use of warm air blowers can assist curing.

Note:

Fuel burning space heaters produce water vapour which will increase humidity and extend curing time. Electric fans, where permissible, are more effective.

Cleaning of Tools:

Clean immediately after use with clean water. Use white spirit or dispose of equipment if the material has dried.

Storage:

12 months under good storage conditions in original, unopened containers at a minimum temperature of 5°C.

PROTECT FROM FROST.



FM 1696
BS EN ISO 9001:2008

Disclaimer - Please read carefully

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, nor its liability for fraud, or fraudulent misrepresentation, nor any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to [Bostik's insurers to advise] the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company. Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products, and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top right hand corner on the front of this document.